



Material Technical Data Sheet

Polypropylene Based Conductive Compound (PPCB)

Property	Nominal Value	Unit	Test Method
Physical			
Specific Gravity	1.03	-	BS2782;509A
Thermal			
Melt Flow Index	30-60	g/10 mins	BS2782:720A 5.0Kg at 230°C
Electrical			
Surface Resistivity	10^5	Ohm	IEC 93

Values are typical properties and are not to be construed as specifications.

ppcb Rev. 0

30 July, 2013